

# General instructions for cleaning and care

## no.5 Polyolefin
















cleaning system with treatment  
end of construction

object \_\_\_\_\_  
address \_\_\_\_\_  
room classification \_\_\_\_\_

date \_\_\_\_\_  
customer \_\_\_\_\_  
representative \_\_\_\_\_

work process: select one work stage from each number

cleaning method	* recommendations chemical products	dosage	* recommendations pad / brush / mop / cloth	recommendations machine / tool	comments
1  dusting damp mopping <input type="checkbox"/>			<b>Masslinn</b> S Microsol cloth S Synthetic fur	<b>Balit with pad sole</b> Balit with velcro	
1  dry vacuum cleaning <input type="checkbox"/>			V S <b>Dust roller nozzle</b> V Combi-nozzle	<b>Twinvac</b> Monovac Portovac	if needed
<b>cleaning without maintenance care product (if coating follows)</b>					
2  wet mopping single step <input type="checkbox"/>	V <b>Ecofloor</b> V Reshine V Antiwax forte classic	<b>0.5 - 1%</b> 1 - 2% 0.5 - 1%	V S <b>Microbrush-mop</b> Microsmooth-mop V S Silkysmooth-mop	<b>Wetbox system</b> Socar / Drewell Wetcar / Drewell	
2  scrubber drying single step <input type="checkbox"/>	V <b>Ecofloor</b> V Reshine V Antiwax forte classic	<b>0.5 - 1%</b> 1 - 2% 0.5 - 1%	● <b>Pad red</b> V ● Pad blue	<b>Duo- / Discomatic</b> Sprinter / Drivematic	
2  wet scrubbing and wet vacuuming <input type="checkbox"/>	V <b>Antiwax forte classic</b> Remat	<b>0.5 - 1%</b> n.a.	● <b>Pad red</b> V ● Pad blue	<b>Monomatic LS</b> <b>Watertank</b> <b>Twinvac / Duovac</b>	heavily soiled  
<b>cleaning with maintenance care (first protective treatment with same product as in maintenance cleaning)</b>					
3  wet mopping single step <input type="checkbox"/>	V <b>Redur</b> Remop	<b>3 - 4%</b> 2 - 3%	V S <b>Microbrush-mop</b> Microsmooth-mop V S Silkysmooth-mop	<b>Wetbox system</b> Socar / Drewell Wetcar / Drewell	
3  scrubber drying single step <input type="checkbox"/>	V <b>Redur</b> Remop	<b>3 - 4%</b> 2 - 3%	● <b>Pad red</b>	<b>Duo- / Discomatic</b> Sprinter / Drivematic	
3  spray cleaning full spray <input type="checkbox"/>	V <b>Polyspray</b> Elspray	<b>100%</b> 100%	● <b>Pad red</b> P ● HS-Polish pad beige P ○ HS-Polish pad white	<b>Monomatic DS</b> <b>Spray unit</b>	after polishing 

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / H: Disinfection / P: polishing / S: structured / V: heavily soiled

important:

# General instructions for cleaning and care

## no.5 Polyolefin



### maintenance cleaning

object \_\_\_\_\_

date \_\_\_\_\_
















address \_\_\_\_\_

customer \_\_\_\_\_

work process: select one work stage from each number

room classification \_\_\_\_\_

representative \_\_\_\_\_

↓	cleaning method	freq uenc	recommendations * chemical products	dosage	recommendations * pad / brush / mop / cloth	recommendations machine / tool	comments
1	 dusting damp mopping	<input type="checkbox"/>			<b>Masslinn</b> S Microsol cloth S Synthetic fur	<b>Balit with pad sole</b> Balit with velcro	Vacuum dry if necessary.
<b>cleaning without maintenance</b>							
2	 wet mopping single step	<input type="checkbox"/>	<b>Ecofloor</b> Reshine Alcosal	<b>0.5 - 1%</b> 1 - 2% 1 - 2%	V S <b>Microbrush-mop</b> Microsmooth-mop Silkysmooth-mop	<b>Wetbox system</b> Wetcar / Drewell Socar / Drewell	
2	 spray mopping (wet mopping)	<input type="checkbox"/>	<b>Ecofloor</b> Reshine Alcosal	<b>0.5 - 1%</b> 1 - 2% 1 - 2%	V <b>Micro nonwoven-1-</b> Micro woven-1- Silkysmooth-1-	<b>Variwet handle</b> <b>Balit with velcro</b> <b>Micro velcro sole</b>	
2	 scrubber drying single step	<input type="checkbox"/>	<b>Ecofloor</b> Reshine Libero	<b>0.5 - 1%</b> 1 - 2% 0.5 - 3%	● <b>Pad red</b> ● Melamine pad	<b>Duo- / Discomatic</b> Sprinter / Drivematic	
2	 polishing, vacuum polishing	<input type="checkbox"/>			B ● <b>HS-Polish pad beige</b> B ○ <b>HS-Polish pad white</b> ● <b>US-Polish pad beige</b>	<b>Monomatic HS</b> <b>Suction ring</b>	0 after polishing 
<b>cleaning with maintenance</b>							
2	 wet mopping single step	<input type="checkbox"/>	<b>Redur</b> Remop	<b>1 - 4%</b> 1 - 2%	V S <b>Microbrush-mop</b> Microsmooth-mop Silkysmooth-mop	<b>Wetbox system</b> Wetcar / Drewell Socar / Drewell	
2	 spray mopping (wet mopping)	<input type="checkbox"/>	<b>Redur</b> Remop	<b>1 - 4%</b> 1 - 2%	V <b>Micro nonwoven-1-</b> Micro woven-1- Silkysmooth-1-	<b>Variwet handle</b> <b>Balit with velcro</b> <b>Micro velcro sole</b>	
2	 scrubber drying single step	<input type="checkbox"/>	<b>Redur</b> Remop	<b>1 - 4%</b> 1 - 2%	● <b>Pad red</b>	<b>Duo- / Discomatic</b> Sprinter / Drivematic	
2	 spray cleaning partial / full spray	<input type="checkbox"/>	<b>Polyspray</b> Elfspray	<b>100%</b> 100%	● <b>Pad red</b> P ● <b>HS-Polish pad beige</b> P ○ <b>HS-Polish pad white</b>	<b>Monomatic DS</b> <b>Spray unit</b>	after polishing 

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / H: Disinfection / P: polishing / S: structured / V: heavily soiled

# General instructions for cleaning and care

no.5  Polyolefin



## interim cleaning

object \_\_\_\_\_

date \_\_\_\_\_














address \_\_\_\_\_

customer \_\_\_\_\_

work process: select one work stage from each number

room classification \_\_\_\_\_

representative \_\_\_\_\_

↓	cleaning method	freq uenc	recommendations * chemical products	dosage	recommendations * pad / brush / mop / cloth	recommendations machine / tool	comments
1	 dusting damp mopping	<input type="checkbox"/>			<b>Massinn</b> S Microsol cloth S Synthetic fur	<b>Balit with pad sole</b> Balit with velcro	
1	dry vacuum cleaning	<input type="checkbox"/>			V S <b>Dust roller nozzle</b> V Combi-nozzle	<b>Monovac</b> Portavac Twinvac	if needed
<b>cleaning without maintenance</b>							
2	 wet mopping two-step	<input type="checkbox"/>	<b>Reshine</b> G Rewit 2000 V Antiwax forte classic	<b>2 - 5%</b> 2 - 5% 2 - 5%	<b>Microsmooth-mop</b> Silkysmooth-mop	<b>Socar / Drewell</b> Wetcar / Drewell	 
2	 scrubber drying two-step	<input type="checkbox"/>	<b>Reshine</b> G Rewit 2000 V Antiwax forte classic	<b>2 - 5%</b> 2 - 5% 2 - 5%	● <b>Pad red</b> ● <b>Pad blue</b>	<b>Duo- / Discomatic</b> Sprinter / Drivematic	 
2	 polishing, vacuum polishing	<input type="checkbox"/>			B ● <b>HS-Polish pad beige</b> B ○ <b>HS-Polish pad white</b> ● <b>US-Polish pad beige</b>	<b>Monomatic HS</b> <b>Suction ring</b>	0 after polishing 
<b>cleaning with maintenance</b>							
2	 spray cleaning full spray	<input type="checkbox"/>	<b>Polyspray</b> Elfspray	<b>100%</b> 100%	● <b>Pad red</b> P ● <b>HS-Polish pad beige</b> P ○ <b>HS-Polish pad white</b>	<b>Monomatic DS</b> <b>Spray unit</b>	after polishing 
2	 US spray cleaning full spray	<input type="checkbox"/>	B <b>US Restorer</b>	<b>100%</b>	● <b>US-Polish pad beige</b>	<b>Monomatic US</b> <b>Spray unit</b>	after polishing 

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / H: Disinfection / P: polishing / S: structured / V: heavily soiled

**important:** For initial cleaning after interim cleaning, see "initial cleaning".

# General instructions for cleaning and care

no.5  Polyolefin



## basic cleaning

object \_\_\_\_\_

date \_\_\_\_\_
































address \_\_\_\_\_

customer \_\_\_\_\_

work process: select one work stage from each number

room classification \_\_\_\_\_

representative \_\_\_\_\_

↓	cleaning method	freq uenc	recommendations * chemical products	dosage	recommendations * pad / brush / mop / cloth	recommendations machine / tool	comments
1	 dusting damp mopping	<input type="checkbox"/>			<b>Masslinn</b> S Microsol cloth S Synthetic fur	<b>Balit with pad sole</b> Balit with velcro	
1	 dry vacuum cleaning	<input type="checkbox"/>			V S <b>Dust roller nozzle</b> V Combi-nozzle	<b>Twinvac</b> Monovac Portavac	if needed
2	 chewing gum removal	<input type="checkbox"/>	<b>Karpfrost</b> Karpotek	<b>100%</b> 100%			if needed 
<b>cleaning without maintenance</b>							
3	 wet scrubbing and wet vacuuming	<input type="checkbox"/>	B <b>Remat forte</b> G Rewit 2000 Antiwax forte classic	<b>10 - 20%</b> 10 - 20% 30 - 50%	V  <b>Pad blue</b>  Pad green	<b>Monomatic I / LS</b> <b>Watertank</b> <b>Twinvac / Duovac</b>	  
3	 scrubber drying two-step	<input type="checkbox"/>	B <b>Remat forte</b> G Rewit 2000 Antiwax forte classic	<b>10 - 20%</b> 10 - 20% 30 - 50%	V  <b>Pad blue</b>  Pad green	<b>Duo- / Discomatic</b> Sprinter / Drivematic	large areas   
3	 spray cleaning full spray	<input type="checkbox"/>	<b>Antiwax forte classic</b>	<b>30 - 50%</b>	V  <b>Pad blue</b>  Pad green	<b>Monomatic I / LS</b> <b>Spray unit</b>	
4	 rinsing	<input type="checkbox"/>		<b>0 100%</b>	 <b>Pad blue</b>  Microsol fibre pad	<b>Monomatic I / LS</b> <b>Twinvac / Duovac</b>	after spray cleaning not necessary.  
4	 rinsing	<input type="checkbox"/>		<b>0 100%</b>	 <b>Pad blue</b>  Microsol fibre pad	<b>Duo- / Discomatic</b> Sprinter / Drivematic	after spray cleaning not necessary.   

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / H: Disinfection / P: polishing / S: structured / V: heavily soiled

**important:** For initial cleaning after basic cleaning, see "initial cleaning".

# General instructions for cleaning and care

no.5  Polyolefin



## protective treatment

object \_\_\_\_\_

date \_\_\_\_\_














address \_\_\_\_\_

customer \_\_\_\_\_

room classification \_\_\_\_\_

representative \_\_\_\_\_

work process: select one work stage from each number

cleaning method	recommendations * chemical products	dosage	recommendations * pad / brush / mop / cloth	recommendations machine / tool	comments
1  dusting  damp mopping <input type="checkbox"/>			S <b>Masslinn 2000</b> S Microsol cloth S Synthetic fur	<b>Balit with pad sole</b> Balit with velcro	
<b>coating</b>					
2  coating <input type="checkbox"/>	<b>Mepol HM</b> Mepol H Mepol HX	100% 100% 100%	<b>Cover for Florfix</b> Florfix-mop	<b>Florfix</b> Balit with velcro	1 - 3 thin layers  
2  waxing <input type="checkbox"/>	<b>Polish</b>	100%	<b>Cover for Florfix</b> Florfix-mop	<b>Florfix</b> Balit with velcro	1 - 3 thin layers  
<b>buffing wax treatment (only if necessary)</b>					
3  dusting  damp mopping <input type="checkbox"/>			S <b>Masslinn 2000</b> S Microsol cloth S Synthetic fur	<b>Balit with pad sole</b> Balit with velcro	
4  polishing, vacuum  polishing <input type="checkbox"/>			C ○ <b>HS-Polish pad white</b>	<b>Monomatic HS</b> <b>Suction ring</b>	0 after polishing 

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / H: Disinfection / P: polishing / S: structured / V: heavily soiled

### important: if needed

before protective treatment: the floor must be perfectly stripped, thoroughly rinsed and completely dry!

Process treatment of protection: see descriptions of method.

For initial cleaning with maintenance cleaner after protective treatment, see "initial cleaning".

## General instructions for cleaning and care

### no. 5 Polyolefin



#### Information about the flooring



Wetrok AG cannot accept any liability for damages due to improper use.  
For security information, see the safety data sheet at [www.wetrok.com](http://www.wetrok.com).  
Wear the required personal protective equipment (PPE): e.g. protective gloves, safety goggles, work shoes.  
Follow the information and remarks on the label, product data sheet and material safety data sheet.  
The product data sheet describes the product and gives information about its application, storage. See [www.wetrok.com](http://www.wetrok.com).  
The recommended colours of pad and brushes consist to the actual wWetrok product range.  
Follow the special cleaning and care instructions of the floor manufacturer.  
The cleaning and care instructions are recommendations and suggestions and apply to floorings in object quality.



**Polyofine floor coverings are scratch-sensitive floor coverings. Do not use abrasive pads or brushes.**  
**Polyofine floor coverings are sensitive to certain solvents, such as ketone, ester and chlorinated hydrocarbon.**  
Fat-soluble colorants such as shoe polish or asphalt can penetrate into polyofine floor coverings: diffusion.  
Polyofine floor coverings are sensitive to cigarette burns, glowing cigarettes and deposit marks.  
Polyofine floor coverings are very resistant to strong alkalines and acids.

Polyofine is an elastic, synthetic, chlorine-free covering made from polyethylene and polypropylene, fillers and colour pigments.  
Polyofine has good electrical insulation properties and often strong electrostatic charges.  
Homogeneous polyofine floor coverings consist of one or more layers with the same composition.  
Heterogeneous polyofine floor coverings consist of several layers with the same basic materials but with a different composition.

Distinguishing feature: fire assay with a glowing hot needle in an inconspicuous place: no acrid smell, crater cannot be removed with the fingers.



Remove loose dirt before every cleaning, damp mop smooth floors and vacuum structured floors.  
Cleaning agents and surface treatments may alter the appearance and properties of a floor's surface.  
Test on an inconspicuous spot to find which product is suitable for your requirements.  
Test beforehand on an inconspicuous spot to see if the cleaning agent or surface treatment damages the floor.  
Dirt-trapping zones, incl. dirt-trapping mats (Wetrok Gardamat) in the entrance, at least 7m long, greatly reduce the amount of dirt tracked into the building.

If you have any questions, please don't hesitate to contact us.  
For training courses, contact the Wetrok Academy, tel. +41 (0)43 255 51 43 or [academy@wetrok.ch](mailto:academy@wetrok.ch).

**Wetrok AG** Steinackerstrasse 62, CH-8302 Kloten, Tel +41 (0)43 255 51 51, [info@wetrok.ch](mailto:info@wetrok.ch), [www.wetrok.com](http://www.wetrok.com)